

## 50 603 AERO TEX

product name:

- AERO TEX.

contains:

- Polyurethane dispersion.

basic information:

- Medium for AERO COLOR® Professional for mixing a textile airbrush colour.

characteristics:

- Improves the adhesion properties on fabrics
- elastic
- light-resistant and non-aging.

handling:

- Shake well before use.
- AERO TEX is ready to use.
- Should be mixed with AERO COLOR® Professional in a ration of 1 : 1.
- Wash, dry and iron the material beforehand.
- Spray application wet.
- After finishing the design let it dry out. Iron the reverse side (cotton about 2 min.; silk / wool about 4 – 6 min.; synthetics about 8 min.; temperature should be adapted to the fabric!).
- Washable at 30 °C; do not dry clean.
- The product can be diluted with water, but dries up to a water-insoluble film.
- Please clean tools as soon as possible with water and/or AERO CLEAN RAPID 50606.
- Best results are achieved with spray application at processing temperatures between 15 and 30 °C, 2 bar air pressure and a nozzle size of > 0,15 mm for coloured shades and 0,3 mm for effect colours.
- Please don't use the product below temperatures under 10 °C object- and room-temperatures.
- Close immediately after use.
- Store in a cool and dry place.
- Protect from frost.
- Individual pre-tests are required (see footer).

product labeling:

- Please refer to the individual safety data sheet on our website [www.schmincke.de](http://www.schmincke.de) or [www.aerocolor.de](http://www.aerocolor.de).

DrK/ 01.07.2014

H. Schmincke & Co. GmbH & Co. KG · Otto-Hahn-Str. 2 · D - 40699 Erkrath ·  
Tel.: +49-211-2509-0 · [www.schmincke.de](http://www.schmincke.de) · [info@schmincke.de](mailto:info@schmincke.de)



The described product characteristics and example applications have been tested at the Schmincke laboratory. The information is based on the technical knowledge and experience which are presently available to us. In view of the diversity of applications with regard to painting techniques, materials and working conditions and the numerous possible influencing factors, the information refers to general areas of application. The information provided here does not constitute a legally binding warranty of specific characteristics or of suitability for a specific application; use of the products is thus to be adapted to the user's special conditions and checked by preliminary tests. We are thus unable to guarantee product characteristics or accept any liability for damage arising in connection with the use of our products.